

Ebenheitstoleranz Klasse N

Dicke	Stahl-Gruppe L		Stahl-Gruppe H	
	Re ≤ 460 MPa		Re >460MPa / <700MPa	
	Messlänge in mm			
	1000	2000	1000	2000
≥ 3 < 5	9	14	12	17
≥ 5 < 8	8	12	11	15
≥ 8 < 15	7	11	10	14
≥ 15 < 25	7	10	10	13
≥ 25 < 40	6	9	9	12
≥ 40 < 250	5	8	8	12
≥ 250 < 400	6	9	9	13

Ebenheitstoleranz Klasse S

Dicke	Stahl-Gruppe L		Stahl-Gruppe H	
	Re ≤ 460 MPa		Re >460MPa / <700MPa	
	Messlänge in mm			
	1000	2000	1000	2000
≥ 3 < 5	5	10	7	14
≥ 5 < 8	5	10	7	13
≥ 8 < 15	3	6	7	12
≥ 15 < 25	3	6	7	11
≥ 25 < 40	3	6	7	11
≥ 40 < 250	3	6	6	10
≥ 250 < 400	4	7	7	11